

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
20 January 2005 (20.01.2005)

PCT

(10) International Publication Number
WO 2005/005495 A2

- (51) International Patent Classification⁷: **C08F 10/00**
- (21) International Application Number:
PCT/EP2004/007061
- (22) International Filing Date: 29 June 2004 (29.06.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
03102001.9 4 July 2003 (04.07.2003) EP
60/486,936 14 July 2003 (14.07.2003) US
- (71) Applicant (for all designated States except US): **BASELL POLYOLEFINE GMBH** [DE/DE]; Brühler Strasse 60, 50389 Wesseling (DE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **TONTI, Maria, Silvia** [IT/IT]; Via Paglia, 1/A, I-44100 Ferrara (IT). **OBERHOFF, Markus** [DE/DE]; Basell Polyolefine GmbH, Paulstrasse 14, 67346 Speyer (DE). **FRAALJE, Volker** [DE/DE]; Basell Polyolefine GmbH, Industriepark Hoechst 104 G 832, 65926 Frankfurt (DE). **BACHMANN, Bernd** [DE/DE]; Basell Polyolefine GmbH, Donaustrasse 26, 64521 Gross-Gerau/Dorn (DE).
- (74) Agent: **COLUCCI, Giuseppe**; Basell Poliolefine Italia S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100 Ferrara (IT).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Declaration under Rule 4.17:**
— of inventorship (Rule 4.17(iv)) for US only
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: OLEFIN POLYMERIZATION PROCESS

(57) Abstract: A process for polymerizing one or more alpha-olefins of formula $\text{CH}_2=\text{CHT}$ wherein T is a hydrogen atom or a $\text{C}_1\text{-C}_{20}$ alkyl radical comprising the following steps: a) contacting in a continuous way one or more of said alpha olefins with a metallocene based catalyst system in a loop reactor, wherein: (i) the reaction is carried out in a liquid medium; (ii) the average residence time of the metallocene-based catalyst system is not more than 30 minutes; (iii) the temperature of the loop ranges from 25° to 70°C; in order to obtain a polymerization degree ranging from 60 to 500 g per gram of catalyst system; b) feeding in continuous the prepolymerized metallocene-based catalyst system obtained in step a) into a polymerization reactor C) polymerizing one or more alpha-olefins, the same or different from the alpha olefins used in step a), in the presence of said prepolymerized metallocene-based catalyst system.